

DERMAGRIP®

High Risk Examination Gloves

Specialty Range

DERMAGRIP High Risk Examination Gloves

DERMAGRIP High Protection Chemo
Examination Gloves

DERMAGRIP High Protection Chemo
Examination Gloves, Sterile

DERMAGRIP-D For Dental & Diagnostic Procedures



Natural Rubber Latex

Powder Free

Extra Protection



Your Partner In Protection™

DERMAGRIP®

High Risk Examination Gloves

www.wrpworld.com

Added Protection
Medical gloves provide protection from unwanted and dangerous substances for both professionals and their patients. **DERMAGRIP® High Risk Examination Gloves** are designed to meet and exceed international product standards using sophisticated technologies and innovations to deliver uncompromized protection to its users.

DERMAGRIP® High Risk Examination Gloves provide unparalleled and added protection in high risk situations. Thicker and stronger than normal examination gloves, these gloves are the ideal choice in situations such as trauma, medical waste handling and decontamination. They are especially suitable for use by emergency response professional such as ambulance attendants, firemen and policemen.

- Powder free to eliminates powder-induced irritation and powder stains
- Textured fingers for enhanced grip
- Thicker for added protection against incidental splash exposure to many types of chemicals
- low levels of NR latex protein and undetectable chemical residues greatly reduce allergic skin reactions
- High tensile strength minimizes tear
- Increased length provides extra protection against debris and splashes
- Beaded cuff ensures easy donning and help prevent roll back



PRODUCT INFORMATION*

Type: Powder free, extra thick, extra long and non-sterile

Primary Material: Natural rubber latex

Dimensions:

Glove Size	Reorder#	Palm Width (mm)	Length (mm)
Small	D1401-14	84	292
Medium	D1402-14	96	295
Large	D1403-14	105	295
Extra-large	D1404-14	117	295

Thickness:

Location of Thickness Measurements	Single Wall (mm)
Finger (at 15 mm from the extreme tip)	0.40
Palm (at center of palm)	0.30
Cuff (at 25 mm from cuff end)	0.20

Physical Properties:

Parameters	Before Aging	After Aging
Tensile Strength (MPa)	29.0	26.0
Elongation (%)	900	860
Modulus 500% (MPa)	2.2	1.9
Force At Break (N)	28.0	26.0

Powder: No powder lubricant added. Light chlorinated on glove surface

Protein Content: This latex glove contains 50 micrograms or less of total water extractable protein per gram of glove

Color: Blue

Design and Feature: Ambidextrous, textured surface overall and beaded cuff

Packing: 50 gloves per dispenser, 10 dispensers per carton

Pre-shipment Quality Inspection:


Criteria	Insp. Level	AQL
Dimension	S-2	4.0
Physical Properties	S-2	4.0
1000ml Water Leak Test	G-I	1.5
Visual Inspection for Major Defects	G-I	2.5
Visual Inspection for Minor Defects	G-I	4.0

Product Conformance:


- Conform to ASTM D3578 and BS EN 455 Parts 1, 2 & 3
- In compliance with European Medical Device Directive 93/42/EEC (CE Class 1)
- In compliance with Personal Protective Equipment Directive 89/686/EEC (Complex Design Category and type tested to EN 420, EN 374-2, EN 374-3 and EN 388)

Quality Assurance: Manufacturing process is in compliance with US FDA Quality System Regulation (QSR) and BS EN ISO9001 Quality System


** The product information provided is a guideline of typical performance values and characteristics of the product and not to be used as actual product specifications.*




BS EN ISO 9001:2000
BRITISH STANDARDS INSTITUTION
CERTIFICATE NO: FM 13934



BS EN 374-2
Micro-organism
Hazards




BS EN 374-3
Chemical
Hazards



BS EN 388
Mechanical
Hazards

0010



COUNCIL DIRECTIVE 93/42/EEC
COUNCIL DIRECTIVE 89/686/EEC



WRP Asia Pacific Sdn Bhd

1 4 7 8 1 7 V

Lot 1, Jalan 3, Kawasan Perusahaan
Bandar Baru Salak Tinggi,
43900 Sepang, Selangor Darul Ehsan,
MALAYSIA

Office +60-3-8706 1486
Facsimile +60-3-8706 1557
Email customer_wrp@wrpworld.com

WRP Asia Pacific Sdn Bhd

CENTRAL EUROPE REGIONAL OFFICE

Grinzing Allee 5/25, 1190 Vienna,
AUSTRIA

Office +43-1-328 4342
Facsimile +43-1-328 2949
Email nare@csi.com

Distributed by: